

TECHNICAL DATA SHEET

en

Name of product:

Bright Aluminium Paint 0156

Type of product: Urethane alkyd-based galvanizing color.

Application: Steel coating, where a galvanized-like surface is required.

Properties: Decorative appearance with a tough surface.

Solids: 55 weight % 45 vol. %

Pre-treatment: Sand blasting in accordance with SA 2½ or chemical pre-treatment in accordance with ISO 8501-1, in addition to, for example, the application of Machine Primer series 0102.

Application:

Method:

Paint Brush

Recommended viscosity:

No thinning required

Thinner:

White spirit can be used to clean paint equipment and, if necessary, for thinning.

Drying:

	Drying time	Film thickness - dry
Dust dry	1 hour 20 °C	30 - 50 µm
Dry to touch	4 hours 20 °C	30 - 50 µm
Dry to recoat	4 hours 20 °C	30 - 50 µm

Recommended coating thickness: Wet film: 90 µm Dry film: 40 µm

Coverage: Theoretical: 11 m²/ltr.

Storage: Store cool and dry

Shelf-life: 12 Months in an unopened container

Cleaning: Tools clean with white spirit 79120.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

EFApaint A/S, Energivej 13, DK-6700 Esbjerg

TLF. +45 75 12 86 00 e-mail: info@efapaint.dk

www.efapaint.dk