

TECHNICAL DATA SHEET**en**

Name of product:

Mirror Finish 0216**Type of product:** Acrylic resin-based paint.**Application:** Protection for the back lining of acrylic mirrors.**Properties:** Good adhesion to plastic and aluminium.**Solids:** 47 weight % 28 vol. %**Application:****Method:**

Conventional spraying

Recommended viscosity:

25-30 sec. DIN-cup 4 mm

Thinner:

0600-86036

Drying:

	Drying time	Film thickness - dry
Dust dry	15 minutes 20 °C	20 - 30 µm
Dry to touch	1 hour 20 °C	20 - 30 µm

Recommended coating thickness: Wet film: 100 µm Dry film: 30 µm**Coverage:** Theoretical: 9 m²/ltr.**Storage:** Store cool and dry**Shelf-life:** 12 Months in an unopened container

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

EFApaint A/S, Energivej 13, DK-6700 EsbjergTLF. +45 75 12 86 00 e-mail: info@efapaint.dkwww.efapaint.dk